

Description

The 8330 *Silver Conductive Epoxy Adhesive: Moderate Cure / Extreme Conductivity* is an electronic grade epoxy that combines moderate curing rate and high conductivity with ease of use. It has a convenient 1-to-1 ratio, a workable ten minutes pot life, and a moderate curing rate. It achieves an operational level in five hours at room temperature. With heat, the 8330 cures in less than 15 minutes and maximizes its conductivity. The cured adhesive bonds very well to most substrates used in electronic assemblies; resists thermal and mechanical shocks; and provides the low resistivity needed for many operating conditions. The 8330 epoxy adhesive is great for forming conductivity seals, bonding, and repairing of electronic devices.

Applications & Usages

The 8330 epoxy has many uses. It is primarily used as a cold solder: a metal solder replacement for bonding heat-sensitive electronic components. It allows for quick cold soldering repairs, and is effective at bonding heat sinks to other components and PCBs. It also provides excellent EMI/RFI shielding, and is very effective at filling in seams between metal plates.

Its primary applications are repair and assembly of electronics in microelectronics and optoelectronics. It is used in the automobile, aerospace, marine communication, instrumentation, and industrial control equipment industries.

Benefits and Features

- **Excellent 0.0006 Ω·cm electrical resistivity and 2.0 W/(m·K) thermal conductivity**
- **Easy 1:1 mix ratio**
- **Adheres to most electronic substrates**
- **Stores and ships at room temperature**—no freezing or dry ice required
- **Very long shelf life of at least two years**—even when stored at room temperature
- **Strong water and chemical resistance** to brine, acids, bases, and aliphatic hydrocarbons

ENVIRONMENT

- ✓ RoHS
- ✓ REACH compliant

Curing & Work Schedule

| <i>Properties</i> | <i>Value</i> |
|--|--------------|
| Working Life ^{a)} | 10 min |
| Shelf Life | ≥3 y |
| Full Cure @25 °C [77 °F] ^{b)} | 5 h |
| Full Cure @65 °C [149 °F] | 15 min |
| Full Cure @80 °C [194 °F] | 10 min |
| Full Cure @120 °C [257 °F] | 7 min |
| Full Cure @160 °C [302 °F] | 5 min |

a) Cure and life values 5 g and room temperature unless stated otherwise.

b) Minimal service cure; for full cure, wait 24 h

Temperature Service Range

| <i>Properties</i> | <i>Value</i> |
|--------------------------------------|--|
| Constant Service Temp. | -40 °C to 150 °C [-40 °F to 302 °F] |
| Storage Temperature of Unmixed Parts | 22 to 27 °C [72 to 80 °F] |

Properties of Cured 8330

| Physical Properties | Method | Value ^{a)} |
|--|----------------------------------|--|
| Color | Visual | Silvery Beige |
| Density @ 26 °C [79 °C] | | 3.10 g/cm ³ |
| Hardness | (Shore D durometer) | 83D |
| Tensile Strength | ASTM D 638 | 13 N/mm ² [1,900 lb/in ²] |
| Elongation | " | — |
| Lap Shear Strength (Stainless Steel 304) | ASTM D 1002 | 1.9 N/mm ² [280 lb/in ²] |
| Compression Strength | ASTM D 695 | 36 N/mm ² [5,200 lb/in ²] |
| Solderable | — | No |
| Water Absorption | ASTM D 570 | 1.34% |
| Outgassing (Total Mass Loss) @ 24 h | ASTM E 595 | 2.87% |
| Water Vapor Release (WVR) | " | 0.13% |
| Collectable Volatile Condensable Material | " | 0.54% |
| Electric Properties | | |
| Volume Resistivity ^{b)} | Method 5011.5 in MIL-STD-883H | 0.0006 Ω·cm |
| Surface Resistance | | |
| After Cure @25 °C for 24 h | Square Probe | 0.07 Ω/sq |
| After Cure @65 °C for 15 min | Square Probe | 0.07 Ω/sq |
| After Cure @80 °C | Square Probe | 0.06 Ω/sq |
| After Cure @120 °C | Square Probe | 0.04 Ω/sq |
| After Cure @160 °C | Square Probe | 0.03 Ω/sq |
| Thermal Properties | | |
| Thermal Conductivity @25 °C | ASTM E 1461 | 1.98 W/(m·K) |
| @50 °C | " | 2.07 W/(m·K) |
| @100 °C | " | 2.03 W/(m·K) |
| Glass Transition Temperature (T _g) | ASTM D 3418 | 53 °C [127 °F] |
| CTE ^{c)} Prior T _g | ASTM E 831 | 89 ppm/°C |
| CTE ^{c)} After T _g | ASTM E 831 | 224 ppm/°C |
| Specific Heat @25 °C [77 °F] | | 0.556 J/(g·K) |

Note: Specifications are for epoxy samples that were cured at 65 °C for 1 hour. Additional curing time at room temperature was given to allow for optimum curing. Samples were conditioned at 23 °C and 50% RH prior to most tests.

a) N/mm² = MPa; lb/in² = psi

b) The uncured epoxy mixture does not conduct electricity well and can have high resistance. To attain stated resistivity, ensure that the mix ratio is followed and that the product is fully cured by heat curing. Room temperature cures may give higher resistivity.

c) Coefficient of Thermal Expansion (CTE) units are in ppm/°C = in/in/°C × 10⁻⁶ = unit/unit/°C × 10⁻⁶



Silver Conductive Epoxy Adhesive Moderate Cure / Extreme Conductivity 8330 Technical Data Sheet

Properties of Uncured 8330

| <i>Physical Property</i> | <i>Mixture (1A:1B)</i> | |
|---------------------------------|------------------------|------------------------|
| Color | Silver Grey | |
| Density ^{a)} | 3.28 g/mL | |
| Mix Ratio by Volume (A:B) | 1:00:1.00 | |
| Mix Ratio by Weight (A:B) | 1.16:1.00 | |
| Solids Content (w/w) | 100% | |
| | | |
| <i>Physical Property</i> | <i>Part A</i> | <i>Part B</i> |
| Color | Silver Grey | Silver Grey |
| Density | 3.45 g/mL | 3.10 g/mL |
| Flash Point | >150 °C [302 °F] | >148 °C [298 °F] |
| Resistivity of Uncured Material | Off-scale (no reading) | Off-scale (no reading) |

a) Calculated value based on measures densities of each part

Principal Components

| Name | CAS Number |
|-----------------------------|--|
| Part A: Bis-A Epoxide Resin | 25068-38-6 |
| Metallic Silver | 7440-22-4 |
| Part B: Aliphatic Amines | 25154-52-3, 1761-71-3, 25154-52-3, 1761-71-3 |
| Metallic Silver | 7440-22-4 |

Compatibility

Adhesion—As seen in the substrate adhesion table, the 8330 epoxy adheres to most materials found on printed circuit assemblies; however, it is not compatible with contaminants like water, oil, and greasy flux residues that may affect adhesion. If contamination is present, clean the printed circuit assembly with electronic cleaner such as MG Chemicals 4050 Safety Wash, 406B Superwash, or 824 Isopropyl Alcohol.

Substrate Adhesion in Decreasing Order

| <i>Physical Properties</i> | <i>Adhesion</i> |
|----------------------------|--------------------------------|
| Steel | Stronger Weaker |
| Aluminum | |
| Fiberglass | |
| Wood | |
| Paper, Fiber | |
| Glass | |
| Rubber | |
| Polycarbonate | |
| Acrylic | |
| Polypropylene ^a | |

a) Does not bond to polypropylene

Storage

Store between 22 and 27 °C [72 and 80 °F] in dry area away from sunlight. Prolonged storage or storage at or near freezing temperatures can result in crystallization. If crystallization occurs, reconstitute the component to its original state by temporarily warming it to 50 to 60 °C [122 to 140 °F]. To ensure full homogeneity, stir thoroughly the warm component, reincorporating all settled material. Re-secure container lid and let cool down before use.

Health, Safety, and Environmental Awareness

Please see the 8330 **Material Safety Data Sheet** (MSDS) parts A and B for more details on transportation, storage, handling and other security guidelines.

Health and Safety: The 8330 parts can ignite if the liquid is both heated and exposed to flames or sparks.

Wear safety glasses or goggles and disposable polyvinyl chloride, neoprene, or nitrile gloves while handling liquids. Part B in particular causes skin burns and may cause sensitization if exposed over a long period of time. The epoxy will not wash off once cured: wear protective work clothing. Wash hands thoroughly after use or if skin contact occurs. Do not ingest.

Use in well-ventilated area since vapors may cause irritation of the respiratory tract and cause respiratory sensitization in susceptible individuals.


The cured epoxy resin presents no known hazard.

Part A

HMIS® RATING

| | |
|-----------------------------|----------|
| HEALTH: | 2 |
| FLAMMABILITY: | 1 |
| PHYSICAL HAZARD: | 0 |
| PERSONAL PROTECTION: | |

NFPA® 704 CODES




Part B

HMIS® RATING

| | |
|-----------------------------|----------|
| HEALTH: | 3 |
| FLAMMABILITY: | 1 |
| PHYSICAL HAZARD: | 0 |
| PERSONAL PROTECTION: | |

NFPA® 704 CODES



Approximate HMIS and NFPA Risk Ratings Legend:

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

Application Instructions

Follow the procedure below for best results. Heat cure is recommended to get the best possible conductivity.

To prepare 1:1 (A:B) epoxy mixture

1. Remove cap or cover.
2. Measure **one** part by volume of **A**.
3. Measure **one** part by volume of **B**.
4. Thoroughly mix the parts together with a stir stick until homogeneous.
5. Apply to with an appropriate sized stick for the application area.

NOTE: Remember to recap the syringe or container promptly after use.

TIP: Due to the high viscosity and abrasiveness of the silver filler, you may preheat part A and part B to increase the flow and improve air release.

To heat cure the 8330 epoxy

Put in oven at 65 °C [149 °F] for 15 minutes.

You can cure the epoxy faster by using higher temperatures of up to 160 °C [302 °F], which will provide a faster cure time of 7 min and optimum conductivity values.

TIP: Hair dryers are normally rated not to exceed 60 °C, so they can generally be used to accelerate the cure.

ATTENTION: Keep the curing temperature well below temperature limit of heat sensitive components that may be present. As a guideline, remember that commercial grade devices normally can be safely operated up to 70 °C, industrial grade up to 85 °C, and military grade up to 175 °C.

ATTENTION: Heat guns can easily exceed the temperature limits for your assembly: they should not be used.

To room temperature cure the 8330 epoxy

Let stand for 5 to 24 hours.

TIP: While the product can be cured at room temperature, the better conductive performance is achieved with heat curing.



ISO 9001 Registered Quality System.
Burlington, Ontario, Canada QMI File # 004008

Silver Conductive Epoxy Adhesive

Moderate Cure / Extreme Conductivity

8330 Technical Data Sheet

8330

Packaging and Supporting Products

Product Availability

| <i>Cat. No.</i> | <i>Form</i> | <i>Net Volume</i> | | <i>Net Weight</i> | | <i>Shipping Weight</i> | |
|------------------|-------------|-------------------|------------|-------------------|---------|------------------------|--------|
| 8330-20G | Liquid | 6 mL | 0.20 fl oz | 20 g | 0.64 oz | 36 g | 1.2 oz |
| 8330-53G | Liquid | 16 mL | 0.55 fl oz | 53 g | 0.12 lb | 75 g | 0.2 lb |
| 8330-606G | Liquid | 184 mL | 6.22 fl oz | 606 g | 1.35 lb | 0.9 kg | 2.0 lb |

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: 1-800-340-0772 Ext. 130 (Canada, Mexico & USA)

1-905-331-1396 Ext. 130 (International)

Fax: 1-905-331-2862 or 1-800-340-0773

Mailing address: **Manufacturing & Support**
1210 Corporate Drive
Burlington, Ontario, Canada
L7L 5R6

Head Office
9347-193rd Street
Surrey, British Columbia, Canada
V4N 4E7

Warranty

M.G. Chemicals Ltd. warrants this product for 12 months from the date of purchase by the end user. *M.G. Chemicals Ltd.* makes no claims as to shelf life of this product for the warranty. The liability of *M.G. Chemicals Ltd.* whether based on its warranty, contracts, or otherwise shall in no case include incidental or consequential damage.

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.